

# BLUESIL FLD 47V50 to 47V1 000

<b>Description</b>	<b>BLUESIL FLD 47V50 to 47V1 000</b> are straight chained polydimethylsiloxanic fluids.
<b>Examples of applications</b>	<p><b>BLUESIL FLD 47V50 to 47V1 000</b> are used as:</p> <ul style="list-style-type: none"> <li>• Thermostatic fluids (– 50 °C to + 200 °C).</li> <li>• Dielectric fluids (impregnation of paper for condensers).</li> <li>• Anti-blotting products for photocopying machines.</li> <li>• Thinning and plastifying agents for RTV's and silicone sealants.</li> <li>• Lubricating and heat protecting agents for textile threads (synthetic sewing threads).</li> <li>• Ingredients in maintenance products (polishes, wax polishes, floor and furniture polishes, etc.).</li> <li>• Paint additives (anti-cratering, anti-floating/flooding and anti-scratching effects, etc.).</li> <li>• Water repellent treatment :                         <ul style="list-style-type: none"> <li>○ of powders (for paints and plastics),</li> <li>○ of fibres : glass fibres.</li> </ul> </li> <li>• Release agents (mould release of plastics and metal castings).</li> <li>• Lubricants (lubrication of elastomers or plastics on metals).</li> <li>• Surfactants for styrene-butadiene foam.</li> </ul>
<b>Key benefits</b>	<p><b>BLUESIL FLD 47V50 to 47V1 000</b> have the following properties:</p> <ul style="list-style-type: none"> <li>• Very good resistance to high and low temperature.</li> <li>• Good combustion resistance.</li> <li>• Good dielectric properties.</li> <li>• Low surface tension.</li> <li>• High compressibility.</li> <li>• Absence of ageing upon exposure to atmospheric agents.</li> <li>• Good oxidation resistance.</li> <li>• Little change in viscosity with temperature.</li> <li>• Good resistance to high and prolonged shear stress.</li> </ul>

## Typical properties

<b>BLUESIL FLD</b>	<b>47V50</b>	<b>47V100</b>	<b>47V300</b>	<b>47V350</b>	<b>47V500</b>	<b>47V1 000</b>
Appearance	Colourless, limpid liquid					
Viscosity at 25°C, mm <sup>2</sup> /s, approx.	50	100	300	350	500	1000
Specific gravity at 25°C, approx.	0.959	0.965	0.970	0.970	0.970	0.970
Flash point (closed cup), °C, approx.	280	≥ 300	≥ 300	≥ 300	≥ 300	≥ 300
Freezing point, °C, approx..	- 55	- 55	- 50	- 50	- 50	- 50
Refractive index at 25°C, approx.	1.402	1.403	1.403	1.403	1.403	1.403
Surface tension at 25°C, mN/m, approx.	20.7	20.9	21.1	21.1	21.1	21.1
Vapour pressure at 200 °C, Pa, approx.	1.33	1.33	1.33	1.33	1.33	1.33

# BLUESIL FLD 47V50 to 47V1 000

Volume expansion coeff. between 25 and 100°C, approx.	1.05.10 <sup>-3</sup>	9.45.10 <sup>-4</sup>	9.45.10 <sup>-4</sup>	9.45.10 <sup>-4</sup>	9.45.10 <sup>-4</sup>	9.45.10 <sup>-4</sup>
Specific heat capacity between 40 and 200°C, J/g, °C	1.46	1.46	1.46	1.46	1.46	1.46
Thermal conductivity, W/m°C, approx.	0.16	0.16	0.16	0.16	0.16	0.16
Viscosity / temperature coeff., approx.	0.59	0.60	0.62	0.62	0.62	0.62
Dielectric strength at 25°C, kV/mm, approx.	15	16	16	16	16	16
Dielectric constant at 25°C between 0.5 and 100 kHz, approx.	2.80	2.80	2.80	2.80	2.80	2.80
Power factor at 25°C, at 100 kHz, approx.	1.10 <sup>-4</sup>	1.10 <sup>-4</sup>	1.10 <sup>-4</sup>	1.10 <sup>-4</sup>	1.10 <sup>-4</sup>	1.10 <sup>-4</sup>
Permittivity at 25°C, W.cm, approx.	1.10 <sup>14</sup>	1.10 <sup>15</sup>	1.10 <sup>15</sup>	1.10 <sup>15</sup>	1.10 <sup>15</sup>	1.10 <sup>15</sup>

Please note: The typical properties are not intended for use in preparing specifications. Please contact our local Sales Department for assistance in writing specifications.

<b>Instruction of use</b>	Please consult your local ELKEM SILICONES sales office.
<b>Regulation</b>	Please consult your local ELKEM SILICONES sales office.
<b>Limitations</b>	Please consult your local ELKEM SILICONES sales office.
<b>Packaging</b>	<ul style="list-style-type: none"> <li>• BLUESIL FLD 47V1 000 is available in                             <ul style="list-style-type: none"> <li>○ Pallet of 1000 KG (2205 LB)</li> <li>○ Drum of 200 KG (441 LB)</li> <li>○ Drum of 25 KG (55.13 LB)</li> </ul> </li> <li>• BLUESIL FLD 47V100 is available in                             <ul style="list-style-type: none"> <li>○ Pallet of 1000 KG (2205 LB)</li> <li>○ Drum of 200 KG (441 LB)</li> </ul> </li> <li>• BLUESIL FLD 47V350 is available in                             <ul style="list-style-type: none"> <li>○ Tote bin of 1000 KG (2205 LB)</li> <li>○ Drum of 200 KG (441 LB)</li> </ul> </li> <li>• BLUESIL FLD 47V50 is available in                             <ul style="list-style-type: none"> <li>○ Tote bin of 1000 KG (2205 LB)</li> <li>○ Drum of 200 KG (441 LB)</li> <li>○ Pail of 20 KG (44.1 LB)</li> </ul> </li> </ul>

# BLUESIL FLD 47V50 to 47V1 000

- BLUESIL FLD 47V500 is available in
  - Pallet of 1000 KG (2205 LB)
  - Drum of 200 KG (441 LB)

## Storage and shelf life

When stored in its original packaging:

BLUESIL FLD 47V1 000 may be stored at temperatures between -20°C / -4°F and 50°C / 122°F for up to 36 months from its date of manufacturing.

BLUESIL FLD 47V100 may be stored at temperatures between -20°C / -4°F and 50°C / 122°F for up to 36 months from its date of manufacturing.

BLUESIL FLD 47V300 may be stored at temperatures between -20°C / -4°F and 50°C / 122°F for up to months from its date of manufacturing.

BLUESIL FLD 47V350 may be stored at temperatures between -20°C / -4°F and 50°C / 122°F for up to 36 months from its date of manufacturing.

BLUESIL FLD 47V50 may be stored at temperatures between -20°C / -4°F and 50°C / 122°F for up to 36 months from its date of manufacturing.

BLUESIL FLD 47V500 may be stored at temperatures between -20°C / -4°F and 50°C / 122°F for up to 36 months from its date of manufacturing.

Comply with the storage instructions and expiration date marked on the packaging. Beyond this date, Elkem Silicones no longer guarantees that the product meets the sales specifications.

## Safety

Please consult the Safety Data Sheet of:

BLUESIL FLD 47V1 000, BLUESIL FLD 47V100, BLUESIL FLD 47V300, BLUESIL FLD 47V350, BLUESIL FLD 47V50 and BLUESIL FLD 47V500

Visit our website [www.elkem.com/silicones/](http://www.elkem.com/silicones/)

### Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELKEM SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELKEM SILICONES is at their disposal to supply any additional information.