

LOCTITE® EDAG PF 455B

November 2025

PRODUCT DESCRIPTION

LOCTITE® EDAG PF 455B provides the following product characteristics:

Technology	Acrylate
Appearance	Translucent green
Product benefits	<ul style="list-style-type: none"> • Non-conductive • Excellent humidity resistance • Excellent printability • Fast UV cure • Excellent adhesion • Good dielectric strength
Cure	Ultraviolet (UV) / Visible light
Application	Non-conductive ink
Typical assembly applications	Insulating crossovers
Key substrates	Treated and Untreated polyester film

LOCTITE® EDAG PF 455B is a UV-curable dielectric ink with good adhesion onto treated and untreated polyester foil. LOCTITE® EDAG PF 455B is screen printable and clear. The coating will show superior humidity resistance and dielectric strength. It will be suitable for the production of crossovers with reduced risk of silver migration and high breakdown voltage. This dielectric is also available as green under the name of LOCTITE® EDAG PF 455BC.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids content, %	100
Viscosity, Brookfield #6SP, 25°C, mPa.s (cP)	
Speed 20 rpm	14,000
Density, g/cm ³	1.02
Theoretical coverage, m ² /kg	
@ 10 µm dry coating thickness	98
Shelf life @ 5 to 25°C, year	
From date of qualification in original seal	1

TYPICAL SCREEN PRINTING PROCESS

Recommended coating thickness

Dry coating thickness, µm	
61 threads/cm screen	25
77 threads/cm screen	18
120 threads/cm screen	10

A 25 to 30µm thickness is recommended for crossovers, applied into two passes, to obtain a pore-free crossover coating.

Emulsion thickness

Emulsion thickness, µm	20 to 40
------------------------	----------

Recommended squeegee

Polyurethane, durometer	70 to 75
-------------------------	----------

Recommended screen type

Monofilament polyester screen, threads/cm	61 to 120
Stainless steel screen, threads/cm	77 to 160

Printing equipment type

Manual
Semi-automatic
High speed reel-to-reel

TYPICAL CURING PERFORMANCE

Recommended UV cure condition

UV lamp 80 Watt/cm or
UV lamp 120 Watt/cm

When applying LOCTITE® EDAG PF 455B as a crossover, two layers of approximately 12 to 15 µm each should be applied. Cure both layers at an energy level of 0.5 Joule/cm² to obtain a good inter-coat adhesion between the first and second layer and to obtain a maximum adhesion of the crossover.

When using LOCTITE® EDAG PF 455B as a crossover, be sure to dry the inks printed over it within 5 minutes. Do not let the ink sprinted over LOCTITE® EDAG PF 455B air dry for extended periods of time.

The above cure profiles are guideline recommendations. These conditions (time and temperature) may vary based on customers' experience and specific application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical properties

Adhesion, grade	5B
Pencil hardness	B

Electrical properties

Sheet resistance, 25µm, Ohm/sq	
4-point probe	not conductive
Breakdown voltage @ 25 µm, volt AC	> 2,700

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use

1. LOCTITE® EDAG PF 455B is supplied ready for use.
2. Should dilution be necessary, use dbutyl glycol acetate (CAS: 112-07-2). Henkel recommends a maximum of 10 wt%. This should be accomplished by adding solvent at 5 wt% intervals until desired viscosity and printability is achieved.
3. Mix thoroughly before use to ensure the entire ink volume is homogenous. A slow speed propeller may be utilized to mix until product is uniform. Avoid rapid stirring as this causes air entrapment.
4. If a gel structure forms after extended storage, the product may be warmed slightly in a water bath (not exceeding 65°C) and stirred.

Clean up

The screen and equipment can be cleaned with dilution solvent, or esters (butylacetate, propylacetate, or ethylacetate), or ketones (MEK, Acetone), or similar solvents.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal storage: 5 to 30°C. Storage below 0°C or greater than 40°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on the specifications of this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.



Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3