

SILISIL RTV MF-Dura 35 Addition-Crosslinking

Description:

SILISIL RTV MF-Dura 35 is a pourable, room-temperature vulcanizing, two-component, addition-based silicone (RTV 2). The product offers the following advantages:

- Vulcanization at room temperature (23 °C)
- Transparent color
- High dimensional accuracy and precision in reproduction
- High mechanical resistance and durability
- No shrinkage
- Excellent tear resistance
- Good compatibility with concrete formulas

Main areas of application:

- Mold making (e.g., jewelry, artificial stones, model making)
- Concrete molds
- Applications where high detail accuracy, tear resistance and dimensional stability are required

Surface preparation:

The surfaces to be reproduced must be clean, dry, and dust-free. Ideally, work at room temperature (approx. 23 °C) to ensure consistent processing and curing times.

Mixture and application:

1. **Preparation:** Shake or stir both components (base and catalyst) well before use to ensure a homogeneous consistency.
2. **Mixing:** Weigh the base and catalyst precisely **by weight in a 1:1 ratio** (maximum tolerance $\pm 5\%$). Mix the components thoroughly, carefully incorporating the mixture into the container walls and bottom.
3. **Venting:** For optimal results, it is recommended to vent the mixture under vacuum after mixing to remove any trapped air bubbles.
4. **Processing:** Pour the mixed silicone slowly, ideally from a height of about 30 cm, into the prepared mold to minimize air bubbles.
5. **Curing:** Vulcanization takes place at room temperature (23 °C). Demolding is possible after approximately 210 minutes. Note that lower temperatures significantly extend the pot life and curing time, while higher temperatures shorten them.

SILISIL RTV MF-Dura 35 Addition-Crosslinking

Technical data:

Color	Translucent
Viscosity of the mixture	7,500 mPa·s (Brookfield)
Density of the mixture	1.09 g/cm ³ (at 23 °C)
Mixing ratio	1:1 by weight
Pot life (at 23 °C)	approximately 20 minutes
Demolding time (at 23 °C)	approximately 210 minutes
Complete curing (at 23 °C)	approximately 24 hours
Hardness (Shore A)	approx. 33 (according to ASTM D 2240)
Tear resistance	>5 N/mm ² (according to ASTM D 412)
Elongation at break	approx. 460 % (according to ASTM D 412)
Tear resistance	20 N/mm (according to ASTM D 624)
Temperature resistance	-40 °C to 200 °C

Packaging:

SILISIL MF-Dura 35 is available as standard in 1 kg + 1 kg, 5 kg + 5 kg, 25 kg + 25 kg and 200 kg + 200 kg containers. Other container sizes are available upon request.

Safety instructions:

Before handling the product, read the safety data sheet and ensure that you have all the information required for safe use.

Important Note:

This document contains information provided to the best of our knowledge and belief, based on the current state of our understanding. This information is for guidance only and does not constitute any obligation on our part, particularly in the event of an infringement of third-party rights through the use of our products. This information should be supplemented by preliminary testing to ensure the product's suitability for its intended purpose.