

BONDERITE L-GP 386 ACHESON

Known as Dag 386
November 2015

PRODUCT DESCRIPTION

BONDERITE L-GP 386 ACHESON provides the following product characteristics:

Technology	Lubricant
Product Type	Graphite dispersion in solvent
Application	Multi purpose

BONDERITE L-GP 386 ACHESON is a colloidal dispersion of graphite in ethyl alcohol. It is used for the formation of dry lubricating films and electrically conducting coatings. It is also employed as an anti-seize material on screw threads.

BONDERITE L-GP 386 ACHESON is used in several metal processing techniques as well, generally spray applied.

BONDERITE L-GP 386 ACHESON is used as billet lubricant in e.g. hot forging of aluminium, orbital forging and cold extrusion.

It is also used as billet front breakthrough lubricant in aluminium extrusion and may be used as protective billet lubricant in warm forming.

BONDERITE L-GP 386 ACHESON is also extensively used as mould pre-treatment in metal casting and as a running-in coating on belts of e.g. Hazlett continuous casting machines.

Special features

- Quick drying
- Good adhesion
- Good lubrication
- Remarkably heat resistant
- Low odour
- Low toxicity
- Dry lubricating film
- Electrically conductive

Application

Dry Film Lubrication

The product is particularly suitable for operation under high loads at normal temperatures, e.g. machines for cigarette manufacture, office machines, vending machines and parking meters.

Electrically Conducting Coatings

Applications include plastic cable treatment, prevention of corona discharge in electrical equipment, as an electrode in radiation meters and counters.

Screw Thread Treatment

BONDERITE L-GP 386 ACHESON dries rapidly to form a dry coating which, unlike pastes, does not attract dirt. The

coating provides constant torque/tension values and prevents seizure. It is applied by brush or dip after dilution to a suitable consistency. It is essential to first clean and degrease the surfaces to be coated.

Other Applications

Pretreatment of anode stubs for aluminium prebake process.

Impregnation of porous materials and incorporation into resins and plastics.

TECHNICAL DATA

(as supplied)

Pigment	graphite
Binder	thermoplastic resin
Solids content, %	~30
Viscosity, mPa.s (Brookfield 20 °C, 20 rpm)	~250
Flash Point, °C	12
Density, kg/m ³	970
Diluent	butanol, butylacetate, ethylalcohol

(as a cured coating)

Coatings will function as dry film lubricants up to maximum temperatures of 250 to 300 °C in air and 1,200 °C in inert atmospheres.

They will provide parting and screw thread anti-seize up to 700°C in air.

The ohmic value may vary from 200 to 1,100 Ohm/square, depending on coating thickness, method of application and drying or curing conditions.

Curing improves adhesion and film strength and increases conductivity.

DIRECTION OF USE**Preliminary Statement**

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Application

After dilution BONDERITE L-GP 386 ACHESON can be applied by spray, brush or dip methods.

For normal use, dilution ratios of 1 part BONDERITE L-GP 386 ACHESON to 2 to 3 parts diluent are recommended but for spraying dilution up to 1: 15 is possible.

Where coatings with good adhesion are required a ratio of 1 : 3 should not be exceeded.

The diluted product should be stirred before use to maintain a homogeneous suspension.

Air dried films are dry to the touch in less than a minute and reach their maximum hardness and conductivity after an hour. Depending on the nature of the substrate the films may be cured for 10 min. to 1 hour, at a maximum temperature of 150 °C.

Disposal

The graphite in BONDERITE L-GP 386 ACHESON may be disposed of as low risk chemical waste or may be burnt. Liquid waste should be collected for solvent generation.

Storage

Recommended Storage Temperature, °C	5 to 30
Shelf-life, months (in unopened original packaging)	24

Classification

Please refer to the corresponding **Material Safety Data**

Sheets for details on:

Hazards identification
Transport information
Regulatory information

ADDITIONAL INFORMATION**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0