

BLUESIL RTV 141 A&B E5

Description	BLUESIL RTV 141 A&B E5 is a two component, polyaddition reaction, room temperature curing silicone elastomer. Curing can be accelerated by heating. After mixing the two components BLUESIL RTV 141 A&B E5 forms a relatively low viscosity, colorless liquid which transforms into an elastic and transparent material once cured. The reaction does not give off any heat.
Examples of applications	<ul style="list-style-type: none"> • Coating or potting protection of electronic components and electrotechnical equipment. • Opto-electronic links. • Insulation of light sensitive cells. • Sheathing of step index optic fibers.
Key benefits	<ul style="list-style-type: none"> • TRANSPARENCY, good optical transmission. • GOOD POURABILITY, for easy filling. • Possibility of adding fillers. • Good reversion resistance in confined spaces.

Typical properties

1. Components of BLUESIL RTV 141 A&B E5

<i>Properties</i>	BLUESIL RTV 141 A E5	BLUESIL RTV 141 B E5
Physical state	Slightly viscous liquid	Slightly viscous liquid
Appearance	Clear or slightly cloudy	Clear or slightly cloudy
Color	Colorless	Colorless
Specific gravity at 25°C, approx.	1.02	1.02
Viscosity at 25°C, mPa.s, approx.	3500	650

2. Mixing the two components

BLUESIL RTV 141 A E5: 100 parts

BLUESIL RTV 141 B E5: 10 parts

Viscosity of RTV 141A&B E5 mixture 25 °C, mPa.s, approx.	4000
Pot life of the catalysed mixture at 25 °C, approx.	4 h
Gellnorm at 50 °C, approx.	40 min

3. Cured compound

3.1. Mechanical properties

Measured after curing 1 hour at 150 °C.

3.1.1. On 6 mm thick specimen

Shore A hardness , points, approx (Standard ASTM D 2240)	50
---	----

3.1.2. On 2 mm thick film

Tensile strength , MPa, approx (Standard AFNOR NF T 46002)	6.0
Elongation at break , %, approx (Standard AFNOR NF T 46002)	120

BLUESIL RTV 141 A&B E5

3.2. Physical properties

Linear shrinkage, %, approx.	1.2
Refractive index, n^{25} approx.	1.406
Volume expansion coefficient, K^{-1}	$9.9 \cdot 10^{-4}$
Thermal conductivity, W(m.K), approx.	0,16
Brittle point, °C, approx. (Standard ASTM D 746)	- 70
Peak thermal withstand, °C, approx.	+ 200

Comment:

Curing at room temperature gives low linear shrinkage (0.4 %), however it stops the cured compound from reaching its optimum mechanical properties.

3.3. Dielectric properties

Dielectric strength, kV/mm, approx. (Standards AFNOR NF C 26225 et CEI 243)	20
Dielectric constant at 1 kHz, approx. (Standards AFNOR C 26 230 et CEI 250)	2.7
Dielectric dissipation factor at 1 kHz, approx. (Standards AFNOR NF C 26 230 et CEI 250)	1.10^{-3}
Volume resistivity, W.cm, approx. (Standards AFNOR NF C 26215 et CEI 93)	1.10^{15}

Please note: The typical properties are not intended for use in preparing specifications. Please contact our local Sales Department for assistance in writing specifications.

Instruction of use

Remix each of the two components (base + catalyst) before each use.

1. Mixing the two components

Add 10 parts of **BLUESIL RTV 141 B E5** to 100 parts of **BLUESIL RTV A E5**. The two components are thoroughly mixed using an electrical or pneumatic mixer, on a low speed setting so as to limit the inclusion of air in the mixture. A dispensing machine can also be used.

2. Degasing

After mixing parts A&B, it is preferable to degas the products to eliminate the air bubbles that would be visible in the finished part and which would reduce the mechanical and dielectrical properties.

Degasing is generally carried out with a vacuum of 30 to 50 mbar releasing the vacuum several times during the operation. This product is particularly long to degas. A recipient with a high diameter/height ratio is better suited to quick degasing however the height must be sufficient to contain the swelling of the elastomer under vacuum conditions.

3. Pouring the mixture

BLUESIL RTV 141 A&B E5 is poured slowly and regularly. In the case of a high thickness coating operation, the casting must be made at the lowest point in the volume to be filled this avoids

BLUESIL RTV 141 A&B E5

forming and including air bubbles in the volume. It should not be filled totally to allow expansion of the RTV at service temperatures.

4. Curing

At 23 °C, demoulding of **BLUESIL RTV 141 A&B E5** is possible after approximately 24 to 48 hours at room temperature. Heat helps to accelerate curing.

Recommended curing temperature:

- 4 hours at 60 °C
- or 2 hours at 100 °C
- or 1 hour at 150 °C

Comment: Certain materials that the RTV may be in contact with when curing could inhibit the reaction:

- Sulphur-containing cured natural and synthetic rubber compounds
- RTV's catalysed with metal salts
- PVC stabilized with tin salts
- Epoxydes catalysed with amines

If in doubt, it is recommended to carry out a test beforehand. It is also recommended to keep special degasing equipment for this type of RTV. Indeed, degasing of other products in the same container could pollute the latter and be detrimental to the curing of **BLUESIL RTV 141 A&B E5**.

5. Adhesion

Adhesion is achieved on most materials using PRIM PMB 821 (after degreasing beforehand with a solvent), applied by immersion or with a brush, then dried for 30 minutes at approx. 25 °C. For optimum adhesion, the RTV must be poured within the following four hours.

Excess primer deteriorates the adhesion level. When PRIM PMB 821 does not give sufficient results, another primer can be recommended, please consult us.

Specific case of repair work:

An object coated in **BLUESIL RTV 141 A&B E5** can be repaired: after cutting, simply make up the volume of elastomer with more, new **BLUESIL RTV 141 A&B E5** which has strong self adhesion without the need for a primer.

Repair of **BLUESIL RTV 141 A&B E5** is invisible in the transparent bulk however, the incision should be made at the last minute to avoid any soiling of the surfaces before the new product is poured in.

Make sure that packaging is hermetically closed again each time it is used.

Regulation	Please consult your local ELKEM SILICONES sales office.
Limitations	Please consult your local ELKEM SILICONES sales office.
Packaging	<ul style="list-style-type: none"> • BLUESIL RTV 141 A E5 is available in <ul style="list-style-type: none"> ○ Drum of 200 KG (441 LB) ○ Pail of 25 KG (55.13 LB) • BLUESIL RTV 141 B E5 is available in <ul style="list-style-type: none"> ○ Pail of 20 KG (44.1 LB) ○ Piece of 2.5 KG (5.51 LB)
Storage and shelf life	When stored in its original packaging: BLUESIL RTV 141 A E5 may be stored at temperatures between -20°C / -4°F and 30°C / 86°F for up to 24 months from its date of manufacturing. BLUESIL RTV 141 B E5 may be stored at temperatures between -20°C / -4°F and 30°C / 86°F for up to 24 months from its date of manufacturing. Comply with the storage instructions and expiration date marked on the packaging. Beyond this date, Elkem Silicones no longer guarantees that the product meets the sales specifications.
Safety	Please consult the Safety Data Sheet of:

BLUESIL RTV 141 A&B E5

BLUESIL RTV 141 A E5 and BLUESIL RTV 141 B E5

Visit our website www.elkem.com/silicones/

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELKEM SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and ELKEM SILICONES is at their disposal to supply any additional information.