

Description **SILICONE PASTE FOR THE CAR** is a polydimethylsiloxanic oil based silicone paste together with inert fillers. This paste is particularly adapted to the protection and insulation of electrical switchgear, notably in extreme temperature conditions.

Examples of applications

- Protection of electrical and electronic switchgear in the aeronautics industry.
- Sealing of electric motors.
- Protection of relays, cable connections, battery terminals, etc.
- Static lubrication of small systems.

Key benefits

- Hydrophobic.
- Chemically inert.
- Good dielectric properties.
- Stability of properties over a wide temperature range.
- Resistance to extreme temperatures: -40°C to $+200^{\circ}\text{C}$
- In conformity with MIL and NATO standards.

Typical properties

	SILICONE PASTE FOR THE CAR
Worked penetration ASTM D 217	
Exudation	
Volatile Content	

1. Physical properties

Colour *	Translucent to whitish
Specific gravity at 25°C	1.0
Penetration worked 60 strokes, 1/10e mm (Standards NF T 6012 - ASTM D 217, DIN 51804)	< 260
Penetration unworked , 24 h-1/10e mm (Standards NF T 6012 - ASTM D 217, DIN 51804)	200
Bleed after 24 h at 200°C	< 6 %
Evaporation after 24 h at 200°C	< 2 %

(*) Note: Slight variations in colour may occur but these do not affect the final properties of the product.

2. Thermal properties

Maximum continuous operating temperature, $^{\circ}\text{C}$: + 200

Minimum continuous operating temperature, $^{\circ}\text{C}$: - 40

Note: These thermal properties are not restrictive: shorter exposure times, when in peak operating conditions authorise use at higher temperatures.

Thermal conductivity at , W/mK: 0.21

SILICONE PASTE FOR THE CAR

Technical Data Sheet n° 757-V2 – 2018/10/29

3. Dielectric properties

Dielectric strength , kV/mm (Standards NF C 26225 - ASTM D 419 - IEC 243)	20
Dielectric constant at 1 kHz (Standards NF C 26230 - ASTM D 150 - IEC 250)	2.6
Power factor 1 kHz (Standards NF C 26230 - ASTM D 150 - IEC 250)	5.10^{-4}
Volume resistivity , .cm(Standards NF C 26215 - ASTM D 257 - IEC 93)	$> 1.10^{13}$

4. Miscellaneous

In conformity with MIL S 8660 C Standard.

Please note: The typical properties are not intended for use in preparing specifications. Please contact our local Sales Department for assistance in writing specifications.

Instruction of use	It is recommended to apply SILICONE PASTE FOR THE CAR onto clean and dry surfaces (degreased if necessary). SILICONE PASTE FOR THE CAR is applied with a brush, with a paint brush, with a spatula or with a paste gun. SILICONE PASTE FOR THE CAR can be diluted in aliphatic or chlorinated solvents to facilitate its application when being applied in thin coats.
Packaging	• BLUESIL PASTE 4 is available in ○ Piece of 1 KG (2.21 LB) ○ Drum of 25 KG (55.13 LB) ○ Piece of 0.1 KG (0.22 LB)
Storage and shelf life	When stored in its original packaging: SILICONE PASTE FOR THE CAR may be stored at a temperature below 40 °C/ 104 °F for up to 36 months from its date of manufacturing. Comply with the storage instructions and expiration date marked on the packaging. Beyond this date, Elkem Silicones no longer guarantees that the product meets the sales specifications.
Regulation	Please consult your local ELKEM SILICONES sales office.
Limitations	Please consult your local ELKEM SILICONES sales office.
Safety	Please consult the Safety Data Sheet of: SILICONE PASTE FOR THE CAR

Visit our website www.silicones.elkem.com

Warning to the users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. ELKEM SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users

